

GRABO

1905

MURAVYL

Technical datasheet

COMMERCIAL

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction		heterogeneous wall covering	
Total thickness	EN ISO 24346	mm	1,5
Wear layer thickness	EN ISO 24340	mm	0,65
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	25
Total weight	EN ISO 23997	kg/m2	1,4
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Residual indentation	EN ISO 24343	max. mm	0,2
Dimensional stability	EN ISO 23999	max. %	0,2
Fire resistance	EN 13501-1	class	Bs2-d0
Chemical resistance	EN ISO 26987		✓
Bacterial resistance	EN ISO 846:1999		✓
Light fastness	EN 20105 B02	grade	6
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes			Phthalate, Solvent and Heavy metal free product
Seaming method			heat or cold weld
CE MARKING	EN 14041		✓

GRABOPLAST Ltd.

H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
info@grabo1905.com www.grabo1905.com