

DOMINO SPC ACOUSTIC *Herringbone*

Technical datasheet

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction	Rigid modular flooring with SPC core		
Total thickness	EN ISO 24346	mm	5,0 + 1,0
Wear layer thickness	EN ISO 24340	mm	0,4
Plank size	EN ISO 24341	mm	151 x 600
Thickness of IXPE foam	EN ISO 24340	mm	1,0
Total weight	EN ISO 23997	kg/m ²	10,5
CLASSIFICATION			
European classification	EN 685	class	23/32/41
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Residual indentation	EN ISO 24343	max. mm	0.1
Dimensional stability	EN ISO 23999	max. %	0.1
Wear resistance IP method A	EN 13329	min. cycles	1 200
Fire resistance	EN 13501-1	class	Bf1-s1
Slip resistance	EN 13893	class	DS
	DIN 51130		R10
Impact sound reduction	EN ISO 717-2	dB	19
Chemical resistance	EN ISO 26987		✓
Light fastness	EN 20105 B02	grade	6
Surface treatment			iGuard PUR Surface
Click system			Uniclick
Environmental attributes			Phthalate, Solvent and Heavy metal free product
Content of PCP	EN 12673		does not contain
Formaldehyde emission	ENV 717-1		E1 (no emission)